

Leather Thickness Conversion Chart

Ounces	Millimeters	Irons	Fractional Inches	Decimal Inches
1	.40	75	$\frac{1}{64}$.016
2	.80	1.50	$\frac{1}{32}$.031
3	1.20	2.25	$\frac{3}{64}$.047
4	1.60	3.00	$\frac{1}{16}$.063
5	2.00	3.75	$\frac{5}{64}$.078
6	2.40	4.50	$\frac{3}{32}$.094
7	2.80	5.25	$\frac{7}{64}$.109
8	3.20	6.00	$\frac{1}{8}$.125
9	3.60	6.75	$\frac{9}{64}$.141
10	4.00	7.50	$\frac{5}{32}$.156
11	4.40	8.25	$\frac{11}{64}$.172
12	4.80	9.00	$\frac{3}{16}$.188